



HDPE PIPE

HDPE EX3 PE100

High Density Polyethylene

Property	Unit	Test Method	Value
MFR(190 C/5Kg)	g/10min	ISO 1133	+ 0.45 - 0.05
MFR(190 C/21.6Kg)	g/10min	ISO 1133	12.0 + 3.0
FRR21.6/5	-	-	28 + 4
Density	g/cm ³	ISO 1133	0.945 + 0.002
Notched Impact Strength	mj/mm ²	ISO179/1eA	> 12
Pipe Evaluation Hydrostatic Strength (80oc,4N/mm ²)	Hours	(DIN 8074 & DIN 8075 & ISO 1167)	1000 min

SURIN